

1. A silicone rubber adhesive composition comprising:

- A. 100 parts by weight of an organopolysiloxane having an average of two or more alkenyl groups per molecule;
- B. an organopolysiloxane having an average of two or more silicon bonded hydrogen atoms in each molecule, in an amount such that the molar ratio of silicon bonded hydrogen atoms in component B to alkenyl groups in component A is from 0.01 to 20;
- C. from 5 to 200 parts by weight of a calcium carbonate powder selected from the group consisting of :
- (i) untreated calcium carbonate;
  - (ii) calcium carbonate treated with an organic acid and,
  - (iii) calcium carbonate treated with an ester of an organic acid,
- said calcium carbonate powder having a BET specific surface area of from 5 to 50 m<sup>2</sup>/g; and
- D. a platinum-based catalyst, in an amount sufficient to effect curing of the composition.

Sub B1

A1

10044199.010902